

SECTION 805 COARSE AGGREGATE

Coarse aggregate shall conform to the requirements of AASHTO M 80 except no gravel, crushed gravel, or crushed concrete shall be used. Also, the requirements of Section 2.1, percentage of wear, Los Angeles Test, shall not be more than 45%. If air-cooled, blast-furnace slag is used, it shall weigh not less than 70 pounds per cubic foot (1.12 metric tons per cubic meter) when tested according to AASHTO T 19/T 19M.