

SECTION 810 ASPHALT CEMENT

Asphalt cement shall be prepared by the refining of crude petroleum using methods conforming to industry standards. The asphalt cement shall conform to the requirements of AASHTO M 226, Table 2.

When tested by ignition, the inorganic insoluble residue content of the asphalt cement shall not exceed 0.25% by weight.