

SECTION 818 MORTAR SAND

Mortar sand shall conform to the requirements of AASHTO M 45 and the following grading:

| <i>Sieve Size</i> | <i>Percent Passing</i> |
|-------------------|------------------------|
| No. 4 (4.75 mm) | 100 |
| No. 8 (2.36 mm) | 95 - 100 |
| No. 100 (150 Fm) | 0 - 25 |
| No. 200 (75 Fm) | 0 - 10 |

Fineness Modulus: 1.6 to 2.5

The organic impurities requirement will be waived for uses other than masonry mortar.