

581.4.01 Limits

General Provisions 101 through 150.

581.5 Payment

The work in this Specification will be paid for on a Lump Sum basis.

Payment is full compensation for:

- Furnishing materials and equipment including structural steel components of the bearings, masonry plates, top plates, sole plates, PTFE, elastomers, anchor bolts, and welding
- Designing the pot bearing
- Performing tests
- Furnishing prototype bearings and test samples
- Performing Work as described and specified in this Specification or the Plans
- Providing incidentals to complete the work

Payment will be made under:

Item No. 581	Pot bearings, bridge No. ____	Per lump sum
--------------	-------------------------------	--------------

581.5.01 Adjustments

General Provisions 101 through 150.

Section 600—Controlled Low Strength Flowable Fill

600.1 General Description

This work consists of furnishing and placing Flowable Fill as an alternate to compacted soil as approved by the Engineer. Applications for this material include beddings, encasements, and closures for tanks and pipe, and general backfill for trenches and abutments.

600.1.01 Definitions

General Provisions 101 through 150.

600.1.02 Related References**A. Standard Specifications**

Section 500—Concrete Structures

Section 801—Fine Aggregate

Section 830—Portland Cement

Section 831—Admixtures

Section 880—Water

B. Referenced Documents

SOP 10

General Provisions 101 through 150.

600.1.03 Submittals

Mix designs for flowable fill, and other documentation listed in Subsection 500.1.03.

600.2 Materials

All materials shall meet the requirements of the following Specifications:

Material	Section
*Fine Aggregate	Subsection 801.2.02
Portland Cement	Subsection 830.2.01
Fly Ash	Subsection 831.2.03
**Air-Entraining Admixtures	Subsection 831.2.01
Water	Subsection 880.2.01

*Note—Gradation requirement is waived.

**Note—High air generators or foaming agents may be used in lieu of conventional air entraining admixtures and may be added at the jobsite and mixed according to the manufacturer's recommendation.

600.2.01 Delivery, Storage, and Handling

General Provisions 101 through 150.

600.3 Construction Requirements

600.3.01 Personnel

General Provisions 101 through 150.

600.3.02 Equipment

General Provisions 101 through 150.

600.3.03 Preparation

A. Mix Design

Flowable fill is a mixture of Portland cement, fly ash, fine aggregate, air entraining admixture, and water. Flowable fill contains a low cementitious content for reduced strength development.

1. Submit mix designs for flowable fill to the Engineer for approval by the Office of Materials and Research. The following table lists mix design proportion ranges for excavatable and non-excavatable flowable fill:

Table 1—Mix Designs for Flowable Fill		
	Excavatable	Non-Excavatable
Cement Type I	75-100 lbs/yd ³ (45-60 kg/m ³)	75-150 lbs/yd ³ (45-90 kg/m ³)
Fly Ash	—	150-600 lbs/yd ³ (90-355 kg/m ³)
Water	*	*
**Air	15 to 35%	5-15%
**28-Day Compressive Strength	Maximum 100 psi (690kPa)	Minimum 125 psi (860 kPa)
**Unit Weight (Wet)	90-100 lbs/ft ³ (1440-1600 kg/m ³)	100-125 lbs/ft ³ (1600-2000 kg/m ³)

*Mix designs shall produce a consistency that will result in a flowable self-leveling product at time of placement.

**The requirements for percent air, compressive strength, and unit weight are for laboratory designs only and are not intended for jobsite acceptance requirements.

600.3.04 Fabrication

Ensure flowable fill is manufactured at plants that qualify as approved sources according to the Standard Operating Procedure for Quality Assurance for Ready-Mix Concrete Plants in Georgia (SOP 10). Mix and deliver according to Subsection 500.2.01 of the Specifications or other methods approved by the Engineer. Revolution counter requirements are waived.

600.3.05 Construction

When using as backfill for pipe, where flotation or misalignment may occur, assure correct alignment of the pipe by using straps, soil anchors, or other approved means of restraint.

Protect flowable fill from freezing for 36 hours after placement.

600.3.06 Quality Acceptance

A. Jobsite Acceptance

Acceptance of flowable fill is based on documentation as outlined in Subsection 500.1.03 of the Specifications and a minimum temperature of flowable fill at the point of delivery of 50 °F (10 °C).

600.3.07 Contractor Warranty and Maintenance

General Provisions 101 through 150.

600.4 Measurement

Flowable fill will be measured for payment in cubic yards (meters) in-place and accepted when shown as a pay item in the Contract. When flowable fill is not shown as a pay item, include the cost of the work in the bid price for the appropriate item.

600.4.01 Limits

General Provisions 101 through 150.

600.5 Payment

When shown as a pay item in the Contract, flowable fill complete, in-place and accepted will be paid for Per cubic yard (meter)

Payment will be made under:

Item No. 600	Flowable fill	Per cubic yard (meter)
--------------	---------------	------------------------

600.5.01 Adjustments

General Provisions 101 through 150.

Section 602—Doublewal™ Precast Wall

602.1 General Description

This work includes the materials, manufacture, construction, measurement, and payment for Doublewal™ precast walls. The scope of work of the wall erection includes:

- Grading for wall construction
- Compacting the wall foundation (including areas underlying the footings and the precast modules)
- Dewatering (general and local) to execute the work properly
- Constructing footings
- Erecting precast concrete modules and caps
- Placing and compacting soils within the Doublewal™ modules
- Excavating and replacing unsuitable materials
- Constructing berms

Ensure that the architectural treatment of the modules is according to the Plan details.

602.1.01 Definitions

Doublewal™—Doublewal™ is a trademark.

602.1.02 Related References

A. Standard Specifications

Section 106—Control of Materials

Section 208—Embankments

Section 500—Concrete Structures