

- h. The allowable tolerances for Type 2 Curb dimensions are as follows:

Measurement Item	Dimension & Tolerance
Thickness	5 ¼ in (131 mm) +/- ¼ in (6mm)
Depth	17 in (425 mm) +/- 1 in (25 mm)
Top Surface	¼ in (6 mm) in 5 ft (1.5 m)
Side Surface	½ in (13 mm) in 5 ft (1.5 m)

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test for Percent Wear according to AASHTO T 96

D. Materials Warranty

General Provisions 101 through 150.

Section 806—Aggregate for Drainage

806.1 General Description

This section includes the requirements for aggregate used for drainage.

806.1.01 Related References

A. Standard Specifications

Section 800 – Coarse Aggregate

B. Referenced Documents

AASHTO T 11

AASHTO T 27

GDT 4

806.2 Materials

806.2.01 Coarse Aggregate for Underdrains

A. Requirements

Use Class A or B coarse aggregate graded for size No. 89 in Table 800.1

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test the aggregate as follows:

Test	Method
Sieve analysis	AASHTO T 27

D. Materials Warranty

General Provisions 101 through 150.

806.2.02 Crushed Stone Drainage Material**A. Requirements**

Use Class A or B coarse aggregate that is graded as follows:

Sieve Size	Percent by Weight
Passing 2 in (50 mm)	100
Passing 1-1/2 in (37.5 mm)	95-100
Passing No. 10 (2 mm)	10-35
Passing No. 100 (150 µm)	0-10

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test the crushed stone as follows:

Test	Method
Sieve analysis	AASHTO T 27

D. Materials Warranty

General Provisions 101 through 150.

806.2.03 Drainage Blanket**A. Requirements**

Use Class A or B coarse aggregate that is graded as follows:

Sieve Size	Percent by Weight
Passing No. 10 (2 mm)	75-100
Passing No. 40 (425 µm)	25-50
Passing No. 60 (250 µm)	0-25
Passing No. 200 (75 µm)	0-8
Percent clay	0-5

B. Fabrication

General Provisions 101 through 150.

C. Acceptance

Test the aggregate as follows:

Test	Method
Sieve analysis	AASHTO T 11 and AASHTO T 27
Percent clay (8 minute elutriation test)	GDT 4

D. Material Warranty

General Provisions 101 through 150.