

**Supplemental Specification
2005 Standard Specification Book**

SECTION 02785M

CHIP SEAL COAT

Delete article 2.6, Table 1 and replace with the following:

Table 1

Chip Seal Cover Material Properties		
Unit Weight	AASHTO T 19	100 lb/ft ³ , max
One Fractured Face	ASTM D 5821	95% min.
Two Fractured Faces	ASTM D 5821	90% min.
LA wear, see Note 1	AASHTO T 96	30% max.
Soundness	AASHTO T 104	10% max.
Flats & Elongates, 1:3 ratio	ASTM D 4791	5% max.
Stripping, see Note 1	Materials MOI 8-945	10% max.
Polishing, see Note 1	AASHTO T 278, T 279	31 min.
Note 1: The Department has the right to waive this requirement if the aggregates have proven acceptable through successful past performance as determined by the Engineer.		