

- (d) **Lime for Soil Stabilization** shall be quicklime or hydrated lime conforming to the requirements of AASHTO M216.

SECTION 241—FLY ASH

241.01—Description.

These specifications cover fly ash (burnt coal residue) used as an additive in hydraulic cement concrete or as a soil stabilizer.

241.02—Detail Requirements.

- (a) **Fly ash used in hydraulic cement concrete** shall conform to the requirements of ASTM C618, Class F or Class C.
- (b) **Fly ash used in lime stabilization** shall conform to the requirements of ASTM C593. Bulk material may be used as approved by the Engineer.

SECTION 242—FENCES

242.01—Description.

These specifications cover material requirements for fence components used in the construction of chain link, pedestrian, barbed wire, woven wire, and lawn fences and material specifications for temporary silt fences, geotextile fabric silt barriers, and filter barriers used for erosion control.

242.02—Detail Requirements.

Unless otherwise specified hereinafter, metallic fence materials shall conform to the requirements of AASHTO M181. Steel posts and braces for standard fence and chain link fence may be fabricated from pregalvanized material in lieu of galvanizing after fabrication provided ends and other areas of exposed metal are satisfactorily repaired using a material conforming to the requirements of Section 233.

- (a) **Chain Link and Pedestrian Fences:** Fabric material shall be 9-gage core, new and shall conform to the following:
1. **Galvanized wire fabric for use in chain link fence** shall be hot dip galvanized after weaving in accordance with the requirements of ASTM A392, Class II, and for use in pedestrian fence shall be hot-