

DIVISION 5 SURFACE TREATMENTS AND PAVEMENTS

5-01 CEMENT CONCRETE PAVEMENT REHABILITATION

5-01.1 Description

This Work consists of rehabilitating or replacing section(s) of Portland cement concrete pavement in accordance with these Specifications and in conformity with the lines, grades, thicknesses, and typical cross-sections shown in the Plans or established by the Engineer.

5-01.2 Materials

Materials shall meet the following requirements as listed:

Portland Cement	9-01
Fine Aggregate	9-03
Coarse Aggregate	9-03
Combined Aggregate	9-03
Joint Filler	9-04.1
Joint Sealants	9-04.2
Reinforcing Steel	9-07
Dowel Bars	9-07.5
Tie Bars	9-07.6
Concrete Patching Material	9-20
Curing Materials and Admixtures	9-23
Water	9-25
Epoxy Resins (bonding agents)	9-26

Parting Compound shall be a curing compound, grease or other substance approved by the Engineer.

Subsealing

Pozzolan meeting the requirements of AASHTO M 295 may also be used.

Standard Mix Design (by volume) for subsealing is as follows:

- 1-part Portland cement Type I or II
- 3-parts pozzolan
- 2.25-parts water

The Contractor shall supply the Engineer with test reports of the slurry to be used on the project. The Contractor shall use the services of a Laboratory that has an equipment calibration/verification system and a technician training and evaluation process per AASHTO R-18 to conduct all tests. The test reports shall show 1, 3, and 7-day strengths, flow cone times, and time of initial set. The 7-day compressive strength shall not be less than 600-psi as measured using AASHTO T-106. Time of efflux shall range from 9 to 15-seconds for the cement concrete pavement slabs and 16 to 25-seconds for the cement concrete bridge approach slabs as per ASTM C939.

The Engineer shall approve any deviation from the standard mix design.

Dowel Bar Retrofit

Dowel bar expansion caps shall be tight fitting and made of non-metallic material, which will allow for ¼-inch of movement at each end of the bar.

Chairs for supporting the dowel bar shall be epoxy coated according to [Section 9-07.3](#) or made from non-metallic material.

The foam insert shall be closed cell foam faced with poster board material or plastic faced material on each side commonly referred to as foam core board by office suppliers. The foam insert shall be capable of remaining in a vertical position and tight to all edges during the placement of the concrete patching material. Caulking filler used for sealing the transverse joint at the bottom and sides of the slot shall be a silicone caulk.

Concrete Patching Material

Concrete Patching Material shall be used for partial depth spall repair, panel replacement and dowel bar retrofit.

5-01.3 Construction Requirements

5-01.3(1)A Concrete Mix Design for Concrete Patching Materials

1. **Materials.** The prepackaged concrete patching material shall conform to [Section 9-20](#). The aggregate extender shall conform to [Section 9-03.1\(4\)](#), AASHTO Grading No. 8.
2. **Submittals and Acceptance.** The Contractor shall use the Manufacturer's recommended proportions for the mix design to be submitted to the Engineer for the concrete patching material. The Contractor's submittal shall include the mix proportions of the prepackaged mix, water, aggregated extender, and the proposed sources for all aggregates. Acceptance shall be based on field verification of the prepackaged patching material, and that the amount of added water and aggregate extender complies with the mix design.

5-01.3(1)B Equipment

In addition to Sections [5-05.3\(3\)A](#), [5-05.3\(3\)B](#), [5-05.3\(3\)D](#) and [5-05.3\(3\)E](#) the following shall apply.

Mobile volumetric mixers shall be calibrated in accordance with [Section 6-09.3\(1\)H](#). The references to the latex admixture shall not apply.

Air compressors shall be of sufficient size and capacity to perform the Work to the satisfaction of the Engineer.

The equipment for grinding cement concrete pavement shall use diamond embedded saw blades gang mounted on a self propelled machine that is specifically designed to smooth and texture concrete pavement. The equipment shall not damage the underlying surface, cause fracture, or spalling of any joints.

All equipment shall be maintained in good condition.

Subsealing

Grout mixers shall consist of a cement injection pump and a high-speed colloidal mixing machine. The colloidal mixing machine shall operate at a minimum speed of 1,200-rpm and shall consist of a rotor operating in close proximity to a stator, creating a high shearing action and subsequent pressure release to make a homogeneous mixture. Water shall be added to the batch through a meter or scale with a totalizer for the day's consumption.

Wooden cylindrical plugs or other devices approved by the Engineer shall be provided to temporarily plug the application holes until the material has set. The plugs shall be slightly tapered on one end for ease in driving.

5-01.3(2) Material Acceptance**5-01.3(2)A Concrete Patching Material**

The concrete patch material shall be as specified in [Section 9-20](#).

5-01.3(2)B Portland Cement Concrete

The point of acceptance will be at the discharge of the placement system.

The concrete producer shall provide a certificate of compliance for each truckload of concrete in accordance with [Section 6-02.3\(5\)B](#).

Acceptance testing for compliance of air content and 28-day compressive strength shall be conducted from samples obtained according to FOP for WAQTC TM 2. Air content shall be determined by conducting WAQTC FOP for AASHTO T 152. If the Contractor fails to provide the Aggregate Correction Factor per WAQTC FOP for AASHTO T 152 with the mix design, one will not be applied. Compressive Strength shall be determined by WSDOT FOP for AASHTO T 22 and WSDOT FOP for AASHTO T 23.

The Contractor shall provide cure boxes in accordance with [Section 6-02.3\(5\)H](#), and protect concrete cylinders in cure boxes from excessive vibration and shock waves during the curing period in accordance with [Section 6-02.3\(6\)D](#). Payment for cure boxes shall be in accordance with [Section 6-02.5](#).

Rejection of Concrete

Rejection by the Contractor: The Contractor may, prior to sampling, elect to remove any defective material and replace it with new material at no expense to the Contracting Agency. The replacement material will be sampled, tested and evaluated for acceptance.

Rejection without Testing: The Engineer may reject any load that appears defective prior to placement. Material rejected before placement shall not be incorporated into the pavement. No payment will be made for the rejected materials unless the Contractor requests that the rejected material be tested. If the Contractor elects to have the rejected materials tested, a sample will be taken and both the air content and strength shall be tested by WSDOT.

Payment for rejected material will be based on the results of the one sample, which was taken and tested. If the rejected material fails either test, no payment will be made for the rejected material and in addition, the cost of sampling and testing, at the rate of \$250.00 per sample shall be borne by the Contractor. If the rejected material passes both tests the mix will be compensated for at actual invoice cost and the cost of the sampling and testing will borne by the Contracting Agency.

5-01.3(3) Subsealing

Subsealing shall not be done when the pavement is wet, or when water is present under the pavement. The maximum surface temperature for testing and subsealing is 70°F.

The Contractor shall test all transverse joints through the areas as shown in the Plans.

The testing will determine the need for subsealing. Testing will be accomplished by applying a 9,000-lb load on each side of the joint to measure the vertical movement (along the right lane edge or the edge nearest the Shoulder). The testing equipment shall be able to record the information to within 0.001-inch. The Contractor shall submit the method of testing, for approval by the Engineer, prior to commencing Work. Testing will

be required before and after the grouting operation. All testing will be conducted when the concrete pavement surface temperature is 70°F or less, except the Engineer shall stop testing earlier if there is evidence of slab lockup due to thermal expansion or as required by other traffic control plans. To determine the location of subsealing, both the leave and approach outside corner of the slab will be tested. Any slab exhibiting a deflection greater than 0.025-inch will be subsealed.

If the slab deflection is greater than 0.025-inch after the initial grouting, a second grouting and third test shall be performed. If the third test fails, the Engineer will make a determination whether to re-grout a third time or to remove the slab.

During the subsealing operation, a positive means of monitoring lift that is accurate to within 0.001-inch, as approved by the Engineer, shall be used. The upward movement of the pavement shall not be greater than 0.025-inch. The maximum allowable pressure for the subseal operation shall not exceed 100-pounds per square-inch, except that a short surge of 300-pounds per square-inch will be allowed when starting to pump the hole in order for the grout to penetrate into the void structure. The pressure shall be monitored by an accurate pressure gauge in the grout line that is protected from the grout slurry. Water displaced from the void structure by grout shall be allowed to flow freely. Excessive loss of the grout through cracks, joints, or from backpressure in the hose or in the Shoulder area will not be allowed.

5-01.3(4) Replace Portland Cement Concrete Panel

Curing, cold weather Work, concrete pavement construction in adjacent lanes, and protection of pavement shall meet the requirements of [Section 5-05.3](#).

Concrete slabs to be replaced as shown in the Plans or staked by the Engineer shall be at least 6.0-feet long and full width of an existing pavement panel. The portion of the panel to remain in place shall have a minimum dimension of 6-feet in length and full panel width; otherwise the entire panel shall be removed and replaced. There shall be no new joints closer than 3.0-feet to an existing transverse joint or crack. A vertical full depth saw cut is required along all longitudinal joints and at transverse locations and, unless the Engineer approves otherwise, an additional vertical full depth relief saw cut located 12-inches to 18-inches from and parallel to the initial longitudinal and transverse saw cut locations is also required. Removal of existing cement concrete pavement shall not cause damage to adjacent slabs that are to remain in place. The Contractor, at no cost to the Contracting Agency, shall repair any damage caused by the Contractor's operation. In areas that will be ground, slab replacements shall be performed prior to pavement grinding.

When new concrete pavement is to be placed against existing cement concrete pavement, epoxy coated tie bars and epoxy coated dowel bars shall be drilled and grouted into the existing pavement with either Type I or IV epoxy resin as specified in [Section 9-26](#). Tie bars are not required for panel replacement less than a full panel.

Dowel bars shall be placed at the mid depth of the concrete slab, centered over the transverse joint, and parallel to the centerline and to the Roadway surface.

Placement tolerances for dowel bars

1. \pm 1-inch of the middle of the concrete slab depth.
2. \pm 1-inch of being centered over the transverse joint.
3. \pm ½-inch from parallel to the centerline.
4. \pm ½-inch from parallel to the Roadway surface.

Dowel bars may be adjusted to avoid contact with existing dowel bars in the transverse joint at approach slabs or existing panels without exceeding specified tolerances.

Tie bars shall be placed at the mid depth of the concrete slab, centered over the joint, perpendicular to centerline, and parallel to the Roadway surface.

Placement tolerances for tie bars

1. ± 1 -inch of the middle of the concrete slab depth.
2. ± 1 -inch of being centered over the joint.
3. ± 1 -inch from perpendicular to the centerline.
4. ± 1 -inch from parallel to the Roadway surface.

The horizontal position of tie bars may be adjusted to avoid contact with existing tie bars in the longitudinal joint where panel replacement takes place.

Dowel bars and tie bars shall be placed according to the Standard Plan when multiple panels are placed.

Panels shall be poured separately from the bridge approach slab.

Dowel bars to be drilled into existing concrete or at a new transverse contraction joint shall have a parting compound, such as curing compound, grease, or other Engineer approved equal, applied to them prior to placement.

The tie bar and dowel bar holes shall be blown clean with compressed air before grouting. The bar shall be centered in the hole for the full length of embedment before grouting. The grout shall then be pumped into the hole around the bar in a manner that the back of the hole will be filled first. Blocking or shimming shall not impede the flow of the grout into the hole. Dams, if needed, shall be placed at the front of the holes to confine the grout. The dams shall permit the escape of air without leaking grout and shall not be removed until grout has cured in the hole.

The Contractor shall smooth the surfacing below the removed panel and compact it to the satisfaction of the Engineer. Crushed surfacing base course, or hot mix asphalt may be needed to bring the surfacing to grade prior to placing the new concrete.

If the material under the removed panel is uncompactable and the Engineer requires it, the Contractor shall excavate the Subgrade 2-feet, place a soil stabilization construction geotextile meeting the requirements of [Section 9-33](#), and backfill with crushed surfacing base course. This Work may include:

1. Furnishing and hauling crushed surfacing base course to the project site.
2. Excavating uncompactable material.
3. Furnishing and placing a soil stabilization construction geotextile.
4. Backfilling and compacting crushed surfacing base course (excluding compacting the surface immediately below the removed panel, if compactable).
5. Removing, hauling and restocking any unused crushed surfacing base course.

Side forms shall meet the requirements of [Section 5-05.3\(7\)B](#) whenever a sawed full depth vertical face cannot be maintained.

The Contractor shall place polyethylene film or building paper in accordance with AASHTO M 171 along all existing concrete surfaces and between the bottom of the slab and treated bases prior to placing concrete.

Grade control shall be the responsibility of the Contractor.

All panels shall be struck off level with the adjacent panels and floated to a smooth surface.

Final finish texturing shall meet the requirements of [Section 5-05.3\(11\)](#).

In areas where the Plans do not require grinding, the surface smoothness will be measured with a 10-foot straightedge by the Engineer in accordance with [Section 5-05.3\(12\)](#). If the replacement panel is located in an area that will be ground as part of portland cement concrete pavement grinding in accordance with [Section 5-01.3\(9\)](#), the surface smoothness shall be measured, by the Contractor, in conjunction with the smoothness measurement done in accordance with [Section 5-01.3\(10\)](#).

All transverse and longitudinal joints shall be sawed and sealed in accordance with [Section 5-05.3\(8\)](#). The Contractor may use a hand pushed single blade saw for sawing joints.

Portland cement concrete shall meet the criteria of Sections [5-05.3\(1\)](#), [5-05.3\(2\)](#) and [5-05.3\(5\)A](#). Where accelerated pavement construction is required the Contractor may use concrete patching materials for panel replacement as specified in [Section 9-20](#).

Opening to traffic shall meet the requirements of [Section 5-05.3\(17\)](#).

5-01.3(5) Partial Depth Spall Repair

Removal of the existing pavement shall not damage any pavement to be left in place. Any existing pavement that is to remain that has been damaged shall be repaired at the Contractor's expense. If jackhammers are used for removing pavement, they shall not weigh more than 30-pounds, and chipping hammers shall not weigh more than 15-pounds. All power driven hand tools used for the removal of pavement shall be operated at angles less than 45-degrees as measured from the surface of the pavement to the tool. The patch limits shall extend beyond the spalled area a minimum of 3.0-inches. Repair areas shall be kept square or rectangular. Repair areas that are within 12.0-inches of another repair area shall be combined.

A vertical saw cut shall be made to a minimum depth of 3.0-inches around the area to be patched as marked by the Engineer. The Contractor shall remove material within the perimeter of the saw cut to a depth of 3.0-inches, or to sound concrete as determined by the Engineer. Repair depths that exceed one third of the total slab shall require full depth repair.

The surface patch area shall be sand blasted and all loose material removed. All sandblasting residue shall be removed using dry oil-free air.

Spall repair shall not be done in areas where dowel bars or heavy reinforcing steel are encountered.

When a partial depth repair is placed directly against an adjacent longitudinal joint, polyethylene film or building paper in accordance with AASHTO M 171 shall be placed between the existing concrete and the area to be patched.

Patches that abut working transverse joints or cracks require placement of a compressible insert. The new joint or crack shall be formed to the same width as the existing joint or crack. The compressible joint material shall be placed into the existing joint 1.0-inch below the depth of repair. The compressible insert shall extend at least 3.0-inches beyond each end of the patch boundaries.

Patches that abut the lane/Shoulder joint require placement of a formed edge, along the slab edge, even with the surface.

The patching material shall be mixed, placed, consolidated, finished and cured according to manufacturer's recommendations. Slab/patch interfaces that will not receive pavement grinding shall be sealed (painted) with a 1:1 cement-water grout along the patch perimeter.

The Contractor shall reseal all joints in accordance with [Section 5-05.3\(8\)B](#).

Opening to traffic shall meet the requirements of [Section 5-05.3\(17\)](#).

5-01.3(6) Dowel Bar Retrofit

Dowel bars shall be installed in the existing concrete pavement joints and transverse cracks where shown in the Plans or as marked by the Engineer.

Saw cut slots will be required in the pavement to place the center of the dowel at mid-depth in the concrete slab. The completed slot shall provide a level, secure surface for the feet of the dowel bar chairs. Slots that intersect longitudinal or random cracks shall not be retrofitted. When gang saws are used, slots that are not used shall be cleaned and sealed with either Type I or IV epoxy resin as specified in Section 9-26. The transverse joint between Portland Cement Concrete Pavement and a Bridge approach slab shall not be retrofitted.

Saw cut slots shall be prepared such that dowel bars can be placed at the mid depth of the concrete slab, centered over the transverse joint, and parallel to the centerline and to the Roadway surface.

Placement tolerances for dowel bars

1. \pm 1-inch of the middle of the concrete slab depth.
2. \pm 1-inch of being centered over the transverse joint.
3. \pm 1/2-inch from parallel to the centerline.
4. \pm 1/2-inch from parallel to the Roadway surface.

If jackhammers are used to break loose the concrete they shall weigh less than 30-pounds.

All slot surfaces shall be cleaned to bare concrete by sand blasting. The cleaning shall remove all slurry, parting compound, and other foreign materials prior to installation of the dowel. Any damage to the concrete shall be repaired by the Contractor at no cost to the Contracting Agency. Traffic shall not be allowed on slots where concrete has been removed.

Prior to placement, the dowel bars shall be lightly coated with a parting compound and placed on a chair that will provide a minimum of 1/2-inch clearance between the bottom of the dowel and the bottom of the slot.

The chair design shall hold the dowel bar tightly in place during placement of the concrete patching material. Immediately prior to placement of the dowel bar and concrete patching material, the Contractor shall caulk the transverse joint or crack at the bottom and sides of the slot as shown in the Plans. The caulking filler shall not be placed any farther than 1/2-inch outside either side of the joint or crack. The transverse joint or crack shall be caulked sufficiently to satisfy the above requirements and to prevent any of the patching material from entering the joint/crack at the bottom or sides of the slot.

A 3/8-inch thick foam insert shall be placed at the middle of the dowel to maintain the transverse joint. The foam insert shall fit tightly around the dowel and to the bottom and edges of the slot and be a minimum of 1 1/2-inch below the existing concrete surface. The foam insert shall be capable of remaining in a vertical position and held tightly to all edges during placement of the patch. If for any reason the foam insert shifts during placement of the patch the Work shall be rejected and redone at the Contractor's expense.

Patching material shall be consolidated by using a 1.0-inch or less diameter vibrator as approved by the Engineer. The Contractor shall not overwork the patching material during the patch consolidation process.

The patching material on the surface of the dowel bar slots shall not be overworked, causing segregation and leaving the fine material on the surface. The patching material shall be left $\frac{1}{8}$ -inch to $\frac{1}{4}$ -inch high and not finished flush with the existing concrete surface.

The joint shall be maintained by saw cutting the surface with a hand pushed single blade saw. The cut width shall be $\frac{3}{16}$ to $\frac{5}{16}$ -inch and the depth $1\frac{1}{2}$ -inches. The cut length shall be $2\frac{1}{4}$ -feet long centered over the 3 retrofit epoxy-coated dowel bars and shall be sawed within 24-hours after placement of the concrete patching material.

Opening to traffic shall meet the requirements of [Section 5-05.3\(17\)](#).

5-01.3(7) Sealing Existing Concrete Random Cracks

The Contractor shall route, clean and seal existing concrete random cracks where indicated by the Engineer. Cracks smaller than $\frac{3}{16}$ -inch in width shall be routed to $\frac{5}{16}$ -inch wide by 1-inch deep prior to placing the sealant. Cracks over $\frac{5}{16}$ -inch in width shall be cleaned and sealed.

All incompressible material shall be completely removed from the existing random crack to a depth of $\frac{3}{4}$ -inch. Immediately prior to sealing, the cracks shall be blown clean with dry, oil free compressed air.

The top surface of the sealant shall be at least $\frac{1}{4}$ -inch below the surface of the pavement.

5-01.3(8) Sealing Existing Transverse and Longitudinal Joints

The Contractor shall clean and seal existing transverse and longitudinal joints where shown in the Plans or as marked by the Engineer.

Old sealant and incompressible material shall be completely removed from the joint to the depth of the new reservoir with a diamond blade saw. The removed sealant shall become the property of the Contractor and be removed from the jobsite.

Removal of the old sealant for the entire depth of the joint is not required if the depth of the new reservoir is less than the depth of the existing joint.

Joints constructed with joint tape do not require cleaning and sealing.

Immediately prior to sealing, the cracks shall be blown clean with dry oil-free compressed air. The joints shall be completely dry before the sealing installation may begin. Immediately following the air blowing, the sealant material shall be installed in conformance to manufacturer's recommendations and in accordance with [Section 5-05.3\(8\)B](#).

The top surface of the sealant shall be at least $\frac{1}{4}$ -inch below the surface of the pavement.

5-01.3(9) Portland Cement Concrete Pavement Grinding

Pavement grinding shall begin within 10-working days of placing dowel bar retrofit patching materials. Once the grinding operation has started it shall be continuous until completed. The right travel lane in the direction of traffic shall be ground first.

The pavement shall be ground in a longitudinal direction beginning and ending at lines normal to the pavement centerline. The minimum overlap between longitudinal passes shall be 2.0-inches. 95-percent of the surface area of the pavement to be ground shall have a minimum of $\frac{1}{8}$ -inch removed by grinding.

Bridge decks, bridge approach slabs and bridge overlay insets shall not be ground. The ground pavement shall be feathered to match the elevation of the above features.

5-01.3(9)A Surface Finish

The final surface texture shall be uniform in appearance with longitudinal corduroy type texture. The grooves shall be between $\frac{3}{32}$ and $\frac{5}{32}$ -inches wide, and no deeper than $\frac{1}{16}$ -inch. The land area between the grooves shall be between $\frac{1}{16}$ and $\frac{1}{8}$ -inches wide.

5-01.3(10) Pavement Smoothness

Perform the Work described in [Section 5-05.3\(12\)](#), and the following:

Where the pavement is ground, calculation of the profile index shall exclude dips and depressions in the existing Roadway. The profilograph generated reports shall be provided to the Engineer prior to payment.

5-01.3(11) Concrete Slurry

All concrete slurry and grinding residue shall be removed from the Roadway on a continual basis immediately behind the grinding or cutting operations. Slurry shall not be allowed to drain across open traffic lanes and Shoulders. Slurry shall not be allowed to drain into any waterway, placed on the Roadway slope within 200-feet of any waterway, or other areas as designated by the Engineer. Prior to commencing grinding or cutting operations, the Contractor shall submit to the Engineer for approval a plan to prevent contaminants, such as grinding slurry or concrete debris, from entering ditches, culverts, or other waterways, including wetlands or aquifers.

Concrete slurry shall be collected from the Roadway and disposed of by the Contractor off the project site. The Contractor shall provide a copy of the permit for an approved waste site for the disposal of the slurry prior to the start of the grinding.

Opening to traffic shall meet the requirements of [Section 5-05.3\(17\)](#).

5-01.4 Measurement

Testing cement concrete pavement slabs for subsealing will be measured per each transverse joint, for each traffic lane tested. Measurement of this item will be made only once and will not be measured again after necessary retesting.

Pavement subseal will be measured by the cubic foot of dry materials.

Retrofit dowel bars will be measured per each for the actual number of bars used in the completed Work.

Cement concrete pavement grinding will be measured by the square yard, based on the actual width and length of area ground. Extra passes to meet the Specifications or overlaps will not be measured.

5-01.5 Payment

Payment will be made in accordance with [Section 1-04.1](#), for each of the following Bid items that are included in the Proposal:

“Testing Cement Concrete Pavement Slabs For Subsealing”, per each.

The unit Contract price per each, when multiplied by the number of units measured, shall be full payment for all costs to complete the testing of all joints located in the areas shown in the Plans. The costs of any retesting required by the Specifications shall also be included.

“Drill Hole for Subsealing”, per each.

“Pavement Subseal”, per cubic foot.

“Replace Cement Concrete Panel”, per square yard.

The unit Contract price per square yard shall be full payment for all costs to complete the Work as specified, including saw cutting full depth, removal and disposal of the existing panels off of the Contracting Agency’s Right of Way, preparing the surfacing below the new panel, provide, place and compact the crushed surfacing or hot mix asphalt, furnishing and placing polyethylene film or building paper, furnishing and placing the portland cement concrete, drilling the holes, providing and anchoring the dowel bars and tie bars, and for all incidentals required to complete the Work as specified.

“Retrofit Dowel Bars”, per each.

The unit Contract price per each shall be full payment for all costs to complete the Work as specified, including furnishing and installing parting compound, dowel bar expansion caps, caulking filler, foam core insert material, cement patch where pavement is removed for dowel bar retrofit and for all incidentals required to complete the Work as specified.

“Partial Depth Spall Repair”, by force account as provided in [Section 1-09.6](#).

To provide a common Proposal for all Bidders, the Contracting Agency has entered an amount in the Proposal to become a part of the total Bid by the Contractor.

“Sealing Existing Concrete Random Crack”, per linear foot.

The unit Contract price per linear foot for “Sealing Existing Concrete Random Crack” shall be full payment for all costs to complete the Work as specified, including removing incompressible material, preparing and sealing existing random cracks where existing random cracks are cleaned and for all incidentals required to complete the Work as specified.

“Sealing Transverse and Longitudinal Joints”, per linear foot.

The unit Contract price per linear foot for “Sealing Transverse and Longitudinal Joints”, shall be full payment for all costs to complete the Work as specified, including removing incompressible material, preparing and sealing existing transverse and longitudinal joints where existing transverse and longitudinal joints are cleaned and for all incidentals required to complete the Work as specified.

“Cement Concrete Pavement Grinding”, per square yard.

The unit Contract price per square yard for “Cement Concrete Pavement Grinding”, when multiplied by the number of units measured, shall be full payment for all costs to complete the Work as specified. The costs of any additional pavement grinding and profiling required to complete the Work as specified is also included in this payment.

“Replace Uncompactable Material”, by force account as provided in [Section 1-09.6](#).

Payment for “Replace Uncompactable Material” will be by force account as provided in [Section 1-09.6](#). For the purpose of providing a common Proposal for Bidders, the Contracting Agency has entered an amount in the Proposal to become a part of the total Bid by the Contractor.

All costs associated with the containment, collection and disposal of concrete slurry and grinding residue shall be included in the applicable concrete grinding or cutting items of Work.